

## Pre-applied adhesive coated metals

**Suitable for use in automotive and many other applications where pre-applied, reactivatable adhesives coatings are required.**

**Key automotive applications include weather strips for the linings of doors, sunroofs, bonnets and boots, body side mouldings and brake shims.**

### Pre-applied adhesives

Firsteel coatings are free of hexavalent chromium and comply with European legislation 2000/53/EC. In general, the product consists of two layers of specially developed resins applied to a metal substrate in a continuous coil-coating operation. As the product is non-tacky, the product can be transported in coil form, is formable and can be reactivated at a later date using either heat or a combination of heat and pressure. The material to be bonded can be applied as an extrusion process, injection forming, in a platen press or rolling operation. The selection of the adhesive and metal substrate will depend on the specific application and manufacturing process. All products are provided with a colour tint to aid identification.

### Reactivation parameters

The manufacturing process will normally involve a pre-heat followed by application of the bonding material and the reactivation process itself. We recommend that the Firsteel product is reheated to a temperature not exceeding that stated in the table 'Typical Properties'. Reactivation temperature windows are also provided.

### Product Types

#### Adhesives for Elastomers

This product is designed to form satisfactory bonds with various grades of unvulcanised elastomers, including styrene butadiene rubber (SBR), nitrile butadiene rubber (NBR), ethylene propylene diene M (EPDM) class polymers, ethylene-propylene rubber (EPR), chloroprene rubber (CR), isoprene rubber (IR) and nitrile rubber (NR).

#### Adhesives for Thermoplastics

This product is designed to form satisfactory bonds with extruded soft and hard polyvinyl chloride (PVC) compounds, polypropylene (PP) and acrylonitrile butadienestyrene (ABS) polymers.

#### Adhesives for Thermoplastic Elastomers (TPE)

This product is designed to form satisfactory bonds with mixes of polypropylene and EPDM and also mixes of polypropylene and talc.

#### Adhesives for general bonding

This is a multipurpose product based on hot-melt technology. The product will form excellent bonds with various materials including metals, plastics such as acrylate, latex, polyester and polyurethane, textiles such as acrylic, cotton, jute and silk, as well as other materials such as cardboard, artificial leather and wood. The product is based on hot melt technology and the bond will be weakened if the end product is exposed to excessive heat.

### Performance

When material supplied by Firsteel is reactivated correctly, it will provide a satisfactory and continuous bond between the metal and the specific material to be bonded. When tested to failure, the overall system will fail within the bonded material and not within the adhesive. Also, the adhesive provides extra corrosion protection and is stable against the presence of solvents and oils. Performance of the bond will depend on the reactivation process, the grade, type and hardness of the material to be bonded, the metal substrate and surface condition or the coated material.

All Firsteel products are flexible and allow for complex cold-forming operations to be performed prior to and following the reactivation and bonding processes without cracking or any other defect of the coating. The product should be stored in a clean, dry environment at a temperature between 5 and 35°C and care should be taken not to damage the surface. Coated material is stable over long periods, with a shelf life from 6 months to 1 year, depending on the grade.

# Pre-applied adhesive coated metals

## Typical properties

	Material to be bonded	Typical film (ECCA T01)	Flexibility (ECCA T07)	Maximum pre-heat temperature (°C)	Reactivation temperature (°C)
Coatings for Elastomers	General elastomers	5-9	0-2.0T	120	150-220
Coatings for Thermoplastics	General PVC	5-10	0-0.5T	110	160-230
	General PVC	3-7	0-1T	150	180-220
	Soft PVC	5-10	0.5-1T	150	180-230
	PP	1-5	0-1.0T	150	180-230
Coatings for Thermoplastic Elastomers	PP	5-10	0.5-1.5T	110	150-200 max.
	General TPE	6-10	0-0.5T	110	170-230
Coatings for General Bonding	Various [1]	20 to 200	0T	-	100-200

[1] Various solutions available for bonding materials such as fabric, wood, fibre etc. Specification dependent on application, please consult Firsteel.

[2] Properties are typical and not offered as a specification. Consult Firsteel as to suitability of these products for a given application.

[3] All figures are based upon target values and do not constitute a specification.

## Decorative products

Metals can be supplied with adhesive on one side and a decorative effect on the other. This allows customised effects or prints to be added to the application in situations where the final product will be visible to the user of the vehicle.

## Substrates

The selection of substrate will depend on factors such as the flexibility, strength and level of corrosion resistance required. Most commonly used substrates are cold rolled (EN 10139) and cold reduced steels (EN 10130), hot dipped galvanised steel (EN 10326, EN10327), aluminium alloys (EN 573/485/515) and stainless steels (EN 10088). Other substrates are available on request.

## Product validation

We can provide recommendations on product selection for a specific process and application. We routinely develop and validate new adhesive technologies. A positive release quality program is operated, ensuring that every batch has adequate bonding and other physical characteristics before the product is despatched.

## Dimensional capability and further processing

Products are available in a range of widths from 6.5mm up to a maximum of 600mm, and in gauges from 0.20mm to 1.40mm for ferrous substrates and 1.60mm for aluminum. Products can be supplied as coils, slit coil or processed blanks. They are also available as traverse wound spools.

Care has been taken to ensure that the contents of this publication are accurate, but Firsteel Limited do not accept responsibility or liability for errors or information that is found to be misleading. Suggestions for, or descriptions of, the end use or application of products or methods of working are for information only and Firsteel Limited and its subsidiaries accept no liability in respect thereof.

Before using products or services supplied or manufactured by Firsteel Limited and its subsidiaries, customers should satisfy themselves as to their suitability.

Copyright Firsteel Limited 2020

**Firsteel Limited**  
Brockhurst Crescent  
Bescot, Walsall  
West Midlands WS5 4AX  
United Kingdom  
T: +44 1922 629 593

[www.firsteel.co.uk](http://www.firsteel.co.uk)

**Registered Office**  
Atlas Centre  
Union Road, West Bromwich  
West Midlands  
B70 9DR  
United Kingdom

Registered in England No: 11863208 VAT Reg No: GB 322 0718 42

